

2Na 104 Exclusive Complex for Foreigners 712 Paeksok-dong, Cheonan-si, Chungchongnam-do,Korea TEL : +82-41-522-1858, FAX : +82-41-522-1857

CUSTOMER : QUANTITY :

TECHNICAL SPECIFICATION DATA SHEET

ITEM	DATA	SPECIFICATION	TEST METHOD
Product No.	6085-03SW		
Reinforcing Fabric	Glass Fabric		
LOT No			
Coating Type	P.T.F.E		
Coated weight Before Adhesive(g/sm)		$135 \pm 5\%$	
Thickness before Adhesive(mm)		0.073	Nominal
Adhesive Thickness (mm)		0.050	Nominal
Adhesive Type		Silicone	
Adhesive Strength(g/2.54cm)		Min. 700	JIS Z 0237
Operating Temperature($^{\circ}$ C)		-73 ~ +260	
Appearance	Good		

Date :

Signed

K.Y.Park IPD Technical Manager

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control.